



## PRODUCT SPECIFICATIONS

### FOAM BOARD ALUFIX

Composed of a complex consisting of 2 sheets coated white paper of 200 Gr./m<sup>2</sup> and an aluminium film of 9 microns between both layers of paper, glued together with an aqueous dispersion of vinyl copolymer.

Thincknesses of 5 and 10 mm.

### COATED WHITE PAPER TWO-SIDED USED IN THE POLYSTERENE COATING

It is started that the papers comply with the technical regulations of the requirements of the following table:

PROPERTY			UNIT	TOLERANCE	GRAMAGE
Gramage	ISO 536	TAPPI T410	g/m <sup>2</sup>	+/- 4%	200
Caliber	ISO 534	TAPPI T411	um	+/- 4%	180
CIE Whiteness	ISO 11475		%	+/- 3%	121.0
Opacity	ISO 2471	TAPPI T519	%	-2.0	97.0
Smoothness Bekk	ISO 5627	TAPPI T475	s		180
Relative Humidity		TAPPI T502	%	+/- 7%	40

Storage time: 2 years provided that the material remains inside the box properly closed with a humidity of +/- 50% and at an ambient temperature of +/- 21/ +/- 25 +/- 5- %.

### PACKAGING

<u>THICKNESS</u>	<u>MEASURE cms.</u>	<u>QUANTITY Sheets/Box</u>
05 mm.	70X100	25
10 mm.	70X100	15
05 mm.	100X140	25
10 mm.	100X140	15
05 mm.	152X305	15
10 mm.	152X305	8