



## PRODUCT SPECIFICATIONS

### FOAM BOARD STANDARD BLACK

Composed of extruded polystyrene black foam inside, covered on both sides with white black paper 180 Gr./m<sup>2</sup> on both sides and stuck together with an aqueous dispersion of vinyl copolymer.

Thicknesses of 5 and 10 mm.

### BLACK PAPER COLOR PLUS BOTH SIDES COATED USED IN THE POLYSTYRENE

Color plus papers stating that meet the technical standards of the requirements of the following table is referenced:

PROPERTY	UNIT	AVERAGE	MAXIMUM	MINIMUM
Gramaje	g/m <sup>2</sup>	181,00	182,00	180,00
Caliber	um	252,50	255,00	250,00
Porosity Bendsten	ml/min	690,00	700,00	680,00
Evenness Bendtsen Canvas	ml/min	550,00	550,00	550,00
Evenness Bendtsen Felt	ml/min	500,00	500,00	500,00
Gluing Cobb 60 Canvas	g/m <sup>2</sup>	30,00	32,00	28,00
Gluing Cobb 60 Felt	g/m <sup>2</sup>	29,00	31,00	27,00

Storage period: 2 years if the material remain inside the box properly closed with a humidity of

+ / - 50% and an ambient temperature of + / - 21 / + / - 2 50 + / 5 -%

### PACKAGING

THICKNESS	MEASURE	QUANTITY Sheets/Box
05 mm.	21x29,7	50
10 mm.	21x29,7	30
05 mm.	29,7x42	25
10 mm.	29,7x42	15
05 mm.	70X100	25
10 mm.	70x100	15
05 mm. 100X200 25 10 mm. 100x200 10		